

# MC-Color Flair pure

Pigmented coating



## PRODUCT PROPERTIES

- Ready-to-use, water-based copolymer dispersion
- Film-forming, matt when dried
- Open to water vapour diffusion and carbonation-retarding
- Colour-proof as resistant to UV and weathering
- Resistant to elevated temperatures, frost and de-icing salts
- Non-flammable, building material class A2-s1, d0 according to EN 13501-1 (product system test)
- Registered with DGNB (Code: SHANCT)
- Resistant to staining
- Application by roller and airless spraying
- Tested and approved as OS 2 and OS 4 surface protection system

## AREAS OF APPLICATION

- Preventive concrete protection for exterior surfaces exposed to weathering
- Surface protection for non-accessible and non-driven-on exterior areas
- Suitable for spray and splash zones of de-icing salts
- REACH-assessed exposure scenarios: periodical water-contact, periodical inhalation, application
- Certified in accordance with EN 1504 part 2 for principles 1, 2 and 8, procedure 1.3, 2.3, 8.3

## APPLICATION ADVICE

**Substrate preparation:** See leaflet “General Application Advice - Surface Protection Systems”.

**Application:** MC-Color Flair pure must be stirred thoroughly prior to application. Application is carried out evenly and crosswise using a short-pile roller or alternatively by airless spraying.

For spray application please ask for our special advice or request the equipment planner “Airless”.

Application must not proceed during rain, high humidity, frost or risk of frost. Freshly applied layers must be protected from dew, rain and frost.

**Standard systems:** MC-Color Flair pure is generally applied in two layers. MC-Color Flair pure may be used in combination with Emcephob WM, Emcephob HC, Nafufill EF, Nafufill KM 103, Nafufill KM 110, Nafufill KM 220, Nafufill KM 110 HS and Nafufill DSP.

**Special system:** On all other substrates priming with MC-Color Primer is necessary prior to application. Afterwards MC-Color Flair pure is applied in two layers.

**Special system:** On all other substrates priming with MC-Color Primer is necessary prior to application. Afterwards MC-Color Flair pure is applied in two layers.

**General information:** Coverage rates depend on condition of the substrate which may lead to over- or under-consumption. Please observe the surface roughness surcharges indicated in the Application Advice. The colouring effect on the object depends on a number of factors, e.g. light, perspective, distance, surrounding and substrate conditions (smooth/rough, absorbent/impervious). The colouring effect is thus often a matter of subjective judgement. We therefore recommend applying a trial area with the chosen system. Adjoining areas should only be coated with material from the same batch.

Depending on the chosen colour, e.g. bright yellow or bright red shades, there might be differences in the opacity and it may therefore be necessary to apply three top coats of MC-Color Flair pure.

## TECHNICAL VALUES & PRODUCT CHARACTERISTICS

Characteristic	Unit	Value	Comments
Density	kg/dm <sup>3</sup>	1.43	
Solids content	Vol.-%	48	
Application conditions	°C	≥ 8 ≤ 30	Temperatura del aire, soporte y material
	%	< 85	rel. humidity
	K	3	above dew point
Consumption 1)	ml/m <sup>2</sup>	220	in 2 passes of 110 ml each
Overworkable after	minutes	approx. 60	Primer / 1st layer
	hours	approx. 4	1st layer / 2nd layer
Rain resistant after	hours	2 - 4	depending on temperature
Dry to the touch after	hour	approx. 1	
Resistance to diffusion (against water vapour H <sub>2</sub> O)	m	0.24	at 118 µm dry layer thickness
Resistance to diffusion (against carbon dioxide CO <sub>2</sub> )	m	270	at 122 µm dry layer thickness

All technical values are laboratory results determined at 21°C ±2°C and 50% relative humidity.

1) The consumption values depend on the impermeability, absorbency and type of substrate. To determine the object-specific consumption quantities, it is advisable to create test areas.

Form	liquid
Delivery form	15 l buckets and 120 l drums
Calculated yield	15 l (for 2 work steps) approx. 68 m <sup>2</sup> ; 120 l (for 2 work steps) approx. 545 m <sup>2</sup>
Storage	Can be stored in cool and dry conditions for at least 24 months in original unopened packs. Protect from frost.
EU Regulation 2004/42 (Decopaint Directive)	RL2004/42/EG All/c (40 g/l) < 40 g/l VOC
Packaging disposal	Make sure single-use containers are completely empty.

**Note:** The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2400020479]