

MC-Fastpack 2300 top

Ductile and flexible injection resin for the durable waterproofing of concrete and masonry



PRODUCT PROPERTIES

- Particularly low-viscosity polyurethane-based elastomer resin
- Very good injectability
- High penetration activity due to low surface tension
- Water-displacing, no foam formation
- Complete curing under dynamic loading
- High elasticity
- Durable water impermeability
- Corresponds to fire class B2 according to DIN 4102 in the injection medium
- CE conformity according to EN 1504-5: CE U(D2) W(1) (1/2/3/4) (5/40)
- General building authority approval issued by the DIBt for injection into soil and groundwater
- REACH exposure: water contact permanent, inhalation periodic, processing and application
- Environmental Product Declaration EPD

AREAS OF APPLICATION

- Ductile, flexible filler and sealant of cracks, construction joints and cavities in concrete and masonry under dry, water-bearing and pressurised water-bearing conditions
- Injection work in accordance with EN 1504-5, DAfStb (repair guidelines), ZTV-ING (contract guidelines for civil engineering works)
- Waterproofing of masonry against moisture penetration and rising damp
- Waterproofing of pipe and liner connections to manhole/shaft structures of sewerage infrastructure
- Sealing injection of manhole ring joints, pipe penetrations, socket joints
- Manual application with the MC-Fastpack Power-Tool

APPLICATION ADVICE

Preparatory measures: Prior to injection, an investigation of the structure and any leaks must be carried out according to the state of the art and the rules of technology and an injection concept must be planned. Packers must be set before injection. A trial injection is recommended.

Mixing the components: Components A and B of MC-Fastpack 2300 top are mixed as they pass through the static mixer of the cartridge system as application proceeds and can be injected directly.

The working time of the resin depends on the ambient temperature. Cooling the cartridges can extend the working time. Heating shortens the working time.

Injection: Two-component injection is implemented with the MC-Fastpack Power-Tool (interchangeable cartridge tray 1:1/2:1) at low injection pressure.

MC-Surface Packer LP or MC-Hammer Packer LP 12 packers are recommended for the injection work.

In case of dimensional tolerances of the mixer tip to the plug-in connection of the packer, the mixer tip can be wrapped with Teflon tape to ensure the tightness of the connection.

Application work should cease once component/substrate temperatures fall below 5 °C.

Ensure compliance with the information given in the specifications and the Safety Data Sheets.

Equipment cleaning: The cartridge system means that the equipment is unlikely to need cleaning. If soiling does occur, all solvent-resistant tools can be cleaned with MC-Cleaner eco or thinner product MC-Verdünnung EP. Material that has reacted or set will need to be removed mechanically.

TECHNICAL VALUES & PRODUCT CHARACTERISTICS

Characteristic	Unit	Value	Comments
Mixing ratio	parts by volume	1 : 1	comp. A : comp. B
Density	kg/dm ³	approx. 1.04	DIN 53479
Viscosity	mPa·s	approx. 55	EN ISO 3219
Working time	minutes	approx. 10	EN 1504-5 (up to 1,000 mPa·s)
Application conditions	°C	5 - 40	component and subsoil temperature
Strain (free)	%	approx. 100	
Strain (in the crack)	%	approx. 11 - 17	EN 12618-2
Tensile strength	N/mm ²	approx. 1.31	EN 12618-1
Surface tension	mN/m	34.651	Krüss Processor, Tensiometer K100
Glass transition temperature	°C	-34.2	EN ISO 11357-2
Expansion (with water)	%	approx. 4	EN 14406

All technical values are laboratory results determined at 21°C ±2°C and 50% relative humidity.

Colour	light brown
Equipment cleaning agent	MC-Verdünnung PU (thinner), under no circumstances should water or aqueous cleaning agents be used
Delivery form	400 ml double-chamber cartridge with a volume ratio of 2 : 1 8 cartridges with 8 static mixers per box.
Storage	Can be stored in original sealed packages at temperatures between 5°C and 35°C in dry conditions for at least 18 months.
Packaging disposal	Make sure single-use containers are completely empty.

Safety instructions

Please note the safety information and advice given on the packaging labels and safety data sheets. GISCODE : PU40

Note: The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2400020511]