

# MC-Fastpack 2700

Rigid sealing injection resin for concrete and masonry



## PRODUCT PROPERTIES

- Low-viscosity polyurethane-based duromer resin
- Good injectability
- Variable control of reactivity
- Water-displacing
- Limited foaming on contact with water (hard foam)
- Durable water impermeability
- High compressive and tensile strength
- Corresponds to fire class B2 according to DIN 4102 in the injection medium
- REACH exposure: water contact permanent, inhalation periodic, processing and application
- Environmental Product Declaration EPD

## AREAS OF APPLICATION

- Sealing and reinforcing of cracked and void-rich structures made of concrete, masonry and natural stone in building construction, civil engineering, hydraulic engineering and general civil engineering
- Waterproofing of concrete and masonry
- Sealing of sheet pile and diaphragm walls
- Waterproofing of pipe and liner connections to manhole/shaft structures of sewerage infrastructure
- Sealing injection of manhole ring joints, pipe penetrations, socket joints
- Sealing of rigid joints in buildings
- Manual application with the MC-Fastpack Power-Tool

## APPLICATION ADVICE

**Preparatory measures:** Prior to injection, an investigation of the structure and any leaks must be carried out according to the state of the art and the rules of technology and an injection concept must be planned. Packers must be set before injection. A trial injection is recommended.

**Mixing the components:** Components A and B of MC-Fastpack 2700 are mixed as they pass through the static mixer of the cartridge system as application proceeds and can be injected directly.

MC-Fastpack 2700 can be injected into structures and foundation soil with and without exposure to water. In contact with or mixed with water, it foams up.

The working time of the resin depends on the ambient temperature. Cooling the cartridges can extend the working time. Heating shortens the working time.

**Injection:** Two-component injection is implemented with the MC-Fastpack Power-Tool (interchangeable cartridge tray 1:1/2:1) at low injection pressure.

MC-Surface Packer LP or MC-Hammer Packer LP 12 packers are recommended for the injection work.

In case of dimensional tolerances of the mixer tip to the plug-in connection of the packer, the mixer tip can be wrapped with Teflon tape to ensure the tightness of the connection.

Application work should cease once component/substrate temperatures fall below 5 °C.

Ensure compliance with the information given in the specifications and the Safety Data Sheets.

**Equipment cleaning:** The cartridge system means that the equipment is unlikely to need cleaning. If soiling does occur, all solvent-resistant tools can be cleaned with MC-Cleaner eco or thinner product MC-Verdünnung EP. Material that has reacted or set will need to be removed mechanically.

## TECHNICAL VALUES & PRODUCT CHARACTERISTICS

Characteristic	Unit	Value	Comments
Mixing ratio	parts by volume	1 : 1	comp. A : comp. B
Density	kg/dm <sup>3</sup>	approx. 1.13	EN ISO 2811-1 mixture
Viscosity (dynamic)	mPa·s	approx. 200	EN ISO 3219 ±50
Flexural stress	N/mm <sup>2</sup>		DIN ISO 178 / at 2%
45 min		approx. 35	
90 min		approx. 42	
24 h		approx. 45	
Working time	seconds	approx. 30	ASTM D7487
Application conditions	°C	5 - 40	component and subsoil temperature
Compressive strength	N/mm <sup>2</sup>	approx. 68	EN ISO 604
Tensile strength	MPa	approx. 60	EN ISO 527-1 (dumbbell tensile specimen)
Expansion factor	%	200 - 1,000	EN 14 406 (dry-wet)
Glass transition temperature	°C	60.4	
Volume change (with water)	%	approx. 200 - 1,000	depending on backpressure

All technical values are laboratory results determined at 21°C ±2°C and 50% relative humidity.

Colour	brown
Equipment cleaning agent	MC-Verdünnung PU (thinner), under no circumstances should water or aqueous cleaning agents be used
Delivery form	400 ml double-chamber cartridge with a volume ratio of 2 : 1 8 cartridges with 8 static mixers per box.
Storage	Can be stored in original sealed packages at temperatures between 5°C and 35°C in dry conditions for at least 18 months.
Packaging disposal	Make sure single-use containers are completely empty.

### Safety instructions

Please note the safety information and advice given on the packaging labels and safety data sheets. GISCODE : PU40

**Note:** The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2400020512]